



正 本
ORIGINAL

試驗報告

日期 Date: 2013.12.10 收件日期 Date of Receipt: 2013.11.29 TEST REPORT

報告編號 Report No.: TAF2K545 數量 Quantity: 1件 報告頁次/頁數 Page Order/Pages: (PI/1) 來文字號 Ref. No.: 空 白

報告抬頭 Report Title: 輝榮企業有限公司(T6245) 試件類別 Item: 針織布

地址 Address: 407 台中市西屯區四川西一街3號

試 驗 項 目			試 驗 結 果	試 驗 方 法
纖維成分			100% Polyester	CNS 2339 L3050-1987
耐洗牢度	變褪色		4-5	CNS 1494 L3027-1999 A-1
	染 污	特多龍	4-5	
		棉	4-5	
水洗尺寸變化 (%)	縱向		+0.4	CNS 13752 L3243-1996
	橫向		+0.1	G法 (30℃) 104 掛乾
現狀支數	表層		79.1 D	CNS 13752 L3243-1996
	裡層		79.0 D	6.7.1
密度 (圈/吋)	經行		43.0	CNS 13752 L3243-1996 6.8
	緯列		49.0	
布重(標準回潮,g/m ²)			134.2	CNS 13752 L3243-1996 6.4.2
乾燥時間 (分鐘)			295	CNS 13752 L3243-1996 6.36.1A (1)溫度:20± 2℃ (2)濕度:65± 5R.H.
吸水高度 (公釐)	縱向		156	CNS 13752 L3243-1996
	橫向		159	6.37.1B
吸水速度 (秒)			0.4	CNS 13752 L3243-1996 6.37.1A

註: "+"表收縮。

註: 依委託者要求水洗尺寸變化的水洗溫度為30℃試驗。

註: 依委託者所提供來樣資料為: YF12024-2 青藍色 72"(針孔內70")220G 吸濕排汗紗


附記: 1.本報告僅對樣品負責,樣品保留期限為一個月。

Note: This report is only responsible for the submitted sample(s), which will be kept for one month period.

2.本報告非經本檢測及驗證部書面同意,不得摘錄複製,但全部複製除外。

This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.

3.試驗報告所載事項不得作為公開廣告及商業推銷之用。
The test report should not be used for public advertisement and commercial promotion.



紡織產業綜合研究所

核 發 人:

resident of

Taiwan Textile Research Institute

紡織所檢測及驗證部 新北市土城區承天路六號

Department of Testing and Certification, Taiwan Textile Research Institute
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R. O. C.)

Tel : +886-2-22670321 ext. 7107, 7110

+886-2-22698229, +886-2-22698230

Fax: +886-2-22675108, +886-2-22689839