



台灣檢驗科技股份有限公司
SGS Taiwan Ltd.

SAMPLE CARD

Inspection, Verification, Testing and Certification

No. 31, Wu Chyuan Road,
WuKu Ind. Zone, Taipei County.

P.O. BOX 312, Taipei, Taiwan


Tel : (886-2)2299 -3939

Fax : (886-2)2299 -3227

Consumer Products Service / Textile Lab

REPORT NO.:

Tx61991A/08



Test Report

報告號碼: TX61991A/2008/TL

日期: 2008 年 08 月 15 日

頁數: 一 之 一 頁

輝榮企業有限公司

台中市西屯區四川西一街 3 號

我們依照客戶的要求,根據客戶送交的樣品進行測試如下:

樣品敘述 : 二塊 100% 棉 丈青色斜紋平織布 分別為(A)和(B)
 收件日期 : 2008 年 06 月 27 日, 08 月 11 日
 測試週期 : 2008 年 06 月 27 日到 07 月 04 日, 08 月 11 日到 08 月 15 日

測試項目 & 測試方法: 依申請者要求進行下列測試

1.纖維成份分析 依日本工業規格協會 JIS L1030-2:2005
 2.紗支數 一般方法檢驗
 3.經緯紗密度 依日本工業規格協會 JIS L1096:1999 Section 8.6
 4.耐水洗染色堅牢度 依日本工業規格協會 JIS L0844:2005 - A-1
 - 水洗溫度 40°C

測試結果:

1.纖維成份分析
 棉 (A)
 100 %
 2.紗支數 (棉支數)
 經紗支數 (B)
 38.2' S
 緯紗支數 22.6' S
 3.經緯紗密度
 經紗根數/每英吋 (B)
 144
 緯紗根數/每英吋 76
 4.耐水洗染色堅牢度
 變褪色 (B)
 4-5 級
 對棉纖維污染度 4-5 級
 對尼龍纖維污染度 4-5 級

備註

此份報告的纖維成份分析測試結果摘錄自報告號碼 TX61991/2008/TL

*** 結 束 ***

台灣檢驗科技股份有限公司

張美華
 主任

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明,此報告結果僅對測試之樣品負責。本報告未經本公司書面許可,不可部份複製。
 This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TW6859791

Test Report

報告號碼: TX61991A/2008/TL

日期: 2008 年 08 月 15 日

頁數: 一 之 一 頁

輝榮企業有限公司

台中市西屯區四川西一街 3 號

我們依照客戶的要求,根據客戶送交的樣品進行測試如下:

樣品敘述 : 二塊 100% 棉 丈青色斜紋平織布 分別為(A)和(B)
 收件日期 : 2008 年 06 月 27 日, 08 月 11 日
 測試週期 : 2008 年 06 月 27 日到 07 月 04 日, 08 月 11 日到 08 月 15 日

測試項目 & 測試方法: 依申請者要求進行下列測試

1.纖維成份分析 依日本工業規格協會 JIS L1030-2:2005
 2.紗支數 一般方法檢驗
 3.經緯紗密度 依日本工業規格協會 JIS L1096:1999 Section 8.6
 4.耐水洗染色堅牢度 依日本工業規格協會 JIS L0844:2005 - A-1
 - 水洗溫度 40°C

測試結果:

1.纖維成份分析

棉

(A)
100 %

2.紗支數 (棉支數)

經紗支數
緯紗支數

(B)
38.2' S
22.6' S

3.經緯紗密度

經紗根數/每英吋
緯紗根數/每英吋

(B)
144
76

4.耐水洗染色堅牢度

變褪色
對棉纖維污染度
對尼龍纖維污染度

(B)
4-5 級
4-5 級
4-5 級

備註

此份報告的纖維成份分析測試結果摘錄自報告號碼 TX61991/2008/TL

*** 結 束 ***

台灣檢驗科技股份有限公司

張美華
主任

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明,此報告結果僅對測試之樣品負責。本報告未經本公司書面許可,不可部份複製。
 This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.